

AGRI-FILM EMBOSSED POLYETHYLENE MULCH FILM STANDARD SPECIFICATION SHEET

TYPICAL VALUES	ASTM TEST METHOD		
Polymer Type	Linear low density Polyethylene (LLDPE)		
Thickness	2.30 mil		
Colour / Finish	black/ embossed		
Impact Resistance	96 g/mil		D 1709/A
Elmendorf Tear Strength	MD	438 g/mil	D 1922
	TD	550 g/mil	
Coefficient of Friction	EXT	0.430	D 1894
	INT	Medium Slip Grade III	
Tensile Strength at Break	MD	3008 psi	D 882
	TD	2907 psi	
Elongation at Break	MD	620%	D 882
	TD	626%	
Standard Perforation	5mm Ø, 150mm O.C.		
Roll Size	1.52m x 366m		