

Terrafix 360R

Product Specifications

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight (Typical)	ASTM D5261	g/m ²	210
Grab Tensile Strength	ASTM D4632	N	712
Grab Elongation	ASTM D4632	%	50-105
Tear Resistance	ASTM D4533	N	267
Puncture CBR ¹	ASTM D4833	N	1820
Permittivity	ASTM D4491	sec ⁻¹	1.50
Water Flow Rate	ASTM D4491	l/min/m ²	4480
Apparent Opening Size	ASTM D4751	mm	0.212
UV Stability	ASTM D4355	% @ 500h	70

1. Burst Strength (Mullen ASTM D3786) and Puncture 1/4" (ASTM D4833) are both replaced by Puncture CBR (ASTM D6241)
*All values are MARV except where specified.