

Terrafix 600R

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight	ASTM D5261	g/m ²	339
Grab Tensile Strength	ASTM D4632	N	1110
Grab Elongation	ASTM D4632	%	50
Tear Resistance	ASTM D4533	N	444
Puncture Resistance	ASTM D4833	N	711
Mullen Burst	ASTM D3786	kPa	3583
Permittivity	ASTM D4491	sec ⁻¹	1.2
Water Flow Rate	ASTM D4491	l/min/m ²	3251
Apparent Opening Size (A.O.S.)	ASTM D4751	mm	0.150
UV Stability	ASTM D4355	% @ 500h	70