

Specification Sheet

Terrafix 800R Nonwoven Geotextile

Terrafix 800R is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers. Terrafix 800R resists ultraviolet deterioration, rotting, biological degradation, naturally encountered bases and acids. Polypropylene is stable within a pH range of 2 to 13.

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Tensile Strength	ASTM D4632	N	1330
Grab Elongation	ASTM D4632	%	50
Tear Resistance	ASTM D4533	N	511
CBR Puncture ¹	ASTM D6241	N	3780
Permittivity	ASTM D4491	sec ⁻¹	1.0
Water Flow Rate	ASTM D4491	l/min/m ²	3055
Apparent Opening Size	ASTM D4751	mm	0.150
UV Stability	ASTM D4355	% @ 500h	70

1. Burst strength (Mullen ASTM D3786) and Puncture (ASTM D4833) are both replaced by CBR Puncture (ASTM D6241)

*All values are MARV except where specified.