

## Material and Performance Specification

# ECSC-2B™ Double Net Straw/Coconut Biodegradable Rolled Erosion Control Product

### Description:

The ECSC-2B™ is made with uniformly distributed 70% agricultural straw, 30% coconut fiber and two organic jute nets securely sewn together with biodegradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECSC-2B™ has functional longevity of approximately 18 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 2:1 to 1:1 and low to medium flow channels. The ECSC-2B™ meets Type 3.B specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

<b>Matrix:</b>	1	2	
	70% Straw	30% Coconut	
<b>Netting:</b>	Type		
Top:	Organic Leno Weave Jute		
Middle:	None		
Bottom:	Organic Leno Weave Jute		
<b>Net Opening:</b>	Top	Middle	
	0.5" x 1.0"	0.5" x 1.0"	
<b>Thread:</b>	Type	Color	
	Biodegradable Threac	Natural	
<b>Roll Sizes:</b>	Standard	"A" Size	Mega
Width:	8 ft 2.4 m	4 ft 1.2 m	16 ft 4.9 m
Length:	112.5 ft 34.3 m	225 ft 68.6 m	112.5 ft 34.3 m
Weight*:	60 lbs 27.2 kg	60 lbs 27.2 kg	120 lbs 54.4 kg
Area:	100 yd <sup>2</sup> 83.6 m <sup>2</sup>	100 yd <sup>2</sup> 83.6 m <sup>2</sup>	200 yd <sup>2</sup> 167.2 m <sup>2</sup>
#/Pallet:	20	6	20

\*Weight at time of manufacturing

### Index Value Properties\*:

Property	Test Method	Typical	
Mass/Unit Area	ASTM D6475	9.00 oz/yd <sup>2</sup>	305.1 g/m <sup>2</sup>
Thickness	ASTM D6525	0.28 in	7.11 mm
Tensile Strength-MD	ASTM D6818	204 lb/ft	2.98 kN/m
Elongation-MD	ASTM D6818	14 %	
Tensile Strength-TD	ASTM D6818	134 lb/ft	1.96 kN/m
Elongation-TD	ASTM D6818	16.3 %	
Light Penetration	ASTM D6567	12 %	
Density / Specific Gravity	ASTM D792	N/A g/cm <sup>3</sup>	
Water Absorption	ASTM D1117	361 %	

\*May differ depending upon raw material variations

### Slope Performance Design Values\*:

Property	Test Method	Value	
C-Factors	ASTM D6459	0.06	
Slope Length (L)	≤ 3:1	3:1-2:1	≥ 2:1
< 50 ft (15 m)	0.055	0.070	0.122
50 ft – 100 ft	0.073	0.101	0.167
>100 ft (30 m)	0.122	0.132	0.212

\*Large-Scale Results obtained by 3<sup>rd</sup> Party GAI Accredited Independent Laboratory

### Bench-Scale Testing\* (NTPEP\*\*\*):

Test Method	Parameters	Results
	50mm (2in) / hr-30 min	SLR**=11.89
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=13.60
	150mm (6in) / hr-30 min	SLR**=15.50
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.46 lb/ft <sup>2</sup>
ECTC Method 4 Germination	Top soil; Fescue; 21 day incubation	671 %

\*Bench scale tests should not be used for design purposes.  
\*\*Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor  
\*\*\*The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

### Channel Performance Design Values\*:

Property	Test Method	Value		
Unvegetated Shear Stress	ASTM D 6460	2.00	lbs/ft <sup>2</sup>	95.76 Pa
Unvegetated Velocity	ASTM D 6460	8.0	ft/s	2.44 m/s
Vegetated Shear Stress	NA	N/A	lbs/ft <sup>2</sup>	N/A Pa
Vegetated Velocity	NA	N/A	ft/s	N/A m/s
Manning's N (Value Represents a Range)		0.029		

\*Large-Scale Results obtained by 3<sup>rd</sup> Party GAI Accredited Independent Laboratory