

Material and Performance Specification

ECX-2™ Double Net Excelsior Rolled Erosion Control Product

Description:

The ECX-2™ is made with uniformly distributed 100% Aspen wood excelsior and two polypropylene nets securely sewn together with degradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECX-2™ has functional longevity of approximately 24 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 2:1 to 1.5:1 and medium to high flow channels. The ECX-2™ meets Type 3.B specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

Matrix:	1	2
	Aspen Wood Excelsior	
Netting:	Type	
	Top: Lightweight Photodegradable Polypropyler	Net Color: Green
	Middle: None	
	Bottom: Lightweight Photodegradable Polypropyler	
Net Opening:	Top	Middle
	0.5" x 0.5"	Bottom: 0.5" x 0.5"
Thread:	Type	Color
	Degradable Threac	White
Roll Sizes:	Standard	"A" Size
	Mega	
Width:	8 ft 2.4 m	4 ft 1.2 m
Length:	112.5 ft 34.3 m	225 ft 68.6 m
Weight*:	64 lbs 29.0 kg	128 lbs 58.1 kg
Area:	100 yd ² 83.6 m ²	200 yd ² 167.2 m ²
#/Pallet:	20	9

*Weight at time of manufacturing

Index Value Properties*:

Property	Test Method	Typical	
Mass/Unit Area	ASTM D6475	9.00 oz/yd ²	305.1 g/m ²
Thickness	ASTM D6525	0.38 in	9.65 mm
Tensile Strength-MD	ASTM D6818	169 lb/ft	2.47 kN/m
Elongation-MD	ASTM D6818	23 %	
Tensile Strength-TD	ASTM D6818	86 lb/ft	1.26 kN/m
Elongation-TD	ASTM D6818	26.0 %	
Light Penetration	ASTM D6567	36 %	
Density / Specific Gravity	ASTM D792	N/A g/cm ³	
Water Absorption	ASTM D1117	171 %	

*May differ depending upon raw material variations

Slope Performance Design Values*:

Property	Test Method	Value	
C-Factors	ASTM D6459	0.04	
Slope Length (L)	≤ 3:1	3:1-2:1	≥ 2:1
< 50 ft (15 m)	0.035	0.144	0.272
50 ft – 100 ft	0.100	0.172	0.377
>100 ft (30 m)	0.210	0.317	0.541

*Large-Scale Results obtained by 3^d Party GAI Accredited Independent Laboratory

Bench-Scale Testing* (NTPPEP***):

Test Method	Parameters	Results
	50mm (2in) / hr-30 min	SLR**=6.69
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=5.18
	150mm (6in) / hr-30 min	SLR**=3.99
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.24 lb/ft ²
ECTC Method 4 Germination	Top soil; Fescue; 21 day incubation	530 %

*Bench scale tests should not be used for design purposes.
 **Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor
 ***The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Channel Performance Design Values*:

Property	Test Method	Value		
Unvegetated Shear Stress	ASTM D 6460	2.13 lbs/ft ²	101.98 Pa	
Unvegetated Velocity	ASTM D 6460	10.7 ft/s	3.26 m/s	
Vegetated Shear Stress	NA	N/A lbs/ft ²	N/A Pa	
Vegetated Velocity	NA	N/A ft/s	N/A m/s	
Manning's N (Value Represents a Range)		0.026		

*Large-Scale Results obtained by 3^d Party GAI Accredited Independent Laboratory