



## 600R Geotextile Specification Sheet

600R is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. 600R resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2-13.

Types of applications for 600R are: Light Coastal Applications / Abrasion Resistance Requirements / Cushion Requirements as well for plastic liners to avoid punctures in a plastic liner such as EPDM, PVC, HDPE.

600R: 24" (inches) maximum rip-rap size / Good abrasion resistance / Medium to high strength at high elongation.

Property	ASTM Test Method	Value Metric Units
<b>Typical Geotextile Properties</b>		
• Weight (Typical)	D 5261	340 g / m <sup>2</sup> (10 oz/sqyd)
• Grab Tensile Strength	D 4632	1110 N
• Grab Elongation	D 4632	50-105 %
• Tear Resistance	D 4533	444 N
• Puncture CBR	D 6241	3110 N
• Permittivity	D 4491	1.2 sec <sup>-1</sup>
• Water Flow	D 4491	3251 l/min/m <sup>2</sup>
• Apparent Opening Size	D 4751	0.180 mm
• U.V. Stability	D 4355	70% @ 500hrs

