

Specification Sheet

Terratrack 200W Woven Geotextile

Terratrack geotextile fabrics are woven polypropylene materials offering optimum performance when used in stabilization applications. Produced from first quality raw materials, they provide the perfect balance of strength and separation in styles capable of functioning exceptionally well in a wide range of performance requirements. Terratrack 200W meets AASHTO M288 Survivability Class 2.

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Tensile Strength	ASTM D4632	N	1350
Grab Elongation	ASTM D6432	%	15
Tear Resistance	ASTM D4533	N	540
CBR Puncture ¹	ASTM D6241	N	4185
Permittivity	ASTM D4491	sec ⁻¹	0.20
Water Flow Rate	ASTM D4491	l/min/m ²	610
Apparent Opening Size	ASTM D4751	mm	0.45
UV Stability	ASTM D4355	% @ 500h	80

1. Burst strength (Mullen ASTM D3786) and Puncture (ASTM D4833) are both replaced by CBR Puncture (ASTM D6241)
*All values are MARV except where specified.